

# FIBRAL<sup>®</sup> Polyester Fibres

Date : 07/03/15

<b>SPECIFICATION ARTICLE 63</b>
---------------------------------

Quality	:	<b>Polyester</b>
First Quality (Y/N)	:	No
Colour	:	raw white
Dtex	:	17 +/-6%
Length	:	64 mm +/-5%
Cross Section	:	round
Tenacity	:	28-34 cN/tex
Elongation	:	55-60 %
Shrinkage	:	<=1% at 160° 15 min dry heat
Elastic Recovery	:	91% +/-5
Crimps	:	>= 3 /cm
Finish	:	0.35% +/-0.05
Density	:	1.38
Melting point	:	250° - 265°

*Present information is given in good faith and is exclusively provided without any guarantee or any liability of our company. The customer only bears the consequences of the use he makes of it. All products not explicitly mentioned as 'first quality', as well as substandard, second choice, regenerated, off-grade material, or waste, are by nature off-specification. They do, for one or another reason, not meet one or more of above specifications.  
Modifications reserved.*