

FIBRAL[®] Polyester Fibres

Date : 06/10/14

SPECIFICATION ARTICLE 15

Quality	:	Polyester
First Quality (Y/N)	:	No
Colour	:	Coco
Dtex	:	77 +/-5
Length	:	64 mm +/- 5
Cross Section	:	round
Tenacity	:	21 cN/tex +/- 1.8
Elongation	:	100 - 110 %
Crimps	:	1.2 - 2 /cm
Finish	:	0.2%
Density	:	1.38
Melting point	:	250° - 265°

Present information is given in good faith and is exclusively provided without any guarantee or any liability of our company. The customer only bears the consequences of the use he makes of it. All products not explicitly mentioned as 'first quality', as well as substandard, second choice, regenerated, off- grade material, or waste, are by nature off-specification. They do, for one or another reason, not meet one or more of above specifications. Modifications reserved.